



tesa® 62934

Product Information



Double-sided PE-foam mounting tape

Product Description

tesa® 62934 is a double-sided PE-foam tape for constructive mounting applications. It consists of a highly conformable PE-foam backing and a tackified acrylic adhesive.

Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

Product Features

- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

Application Fields

- Decorative aluminium cover screens on brown goods
- Doorhandles in kitchen furniture
- Moulded plastic parts
- Mirrors and coloured glass panels

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-------------|
| • Backing material | PE foam | • Total thickness | 800 µm |
| • Type of adhesive | tackified acrylic | • Colour | black/white |



tesa® 62934

Product Information

Properties/Performance Values

• Elongation at break	250 %	• Static shear resistance at 40°C	good
• Tensile strength	8 N/cm	• Tack	good
• Ageing resistance (UV)	good	• Temperature resistance long term duration	80 °C
• Static shear resistance at 23°C	good	• Temperature resistance short term duration	80 °C

Adhesion to Values

• ABS (initial)	17 N/cm	• PET (after 14 days)	17 N/cm
• ABS (after 14 days)	17 N/cm	• PP (initial)	2.8 N/cm
• Aluminium (initial)	17 N/cm	• PP (after 14 days)	5.5 N/cm
• Aluminium (after 14 days)	17 N/cm	• PS (initial)	15 N/cm
• PC (initial)	15 N/cm	• PS (after 14 days)	17 N/cm
• PC (after 14 days)	17 N/cm	• PVC (initial)	17 N/cm
• PE (initial)	2.7 N/cm	• PVC (after 14 days)	17 N/cm
• PE (after 14 days)	2.8 N/cm	• Steel (initial)	17 N/cm
• PET (initial)	12.5 N/cm	• Steel (after 14 days)	17 N/cm

Additional Information

Liner variants:

PV0 brown glassine paper (71 µm)

PV14 white PE-coated paper (120 µm)

PV10 red filmic liner (120 µm)

tesa® 62934 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 / 61646 climate tests and a 85°C temperature resistance. (TÜV report number 21209595).

Peel Adhesion:

- immediate: foam splitting on Steel, Aluminium, ABS

- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=62934>